



## INDUSTRIAL RAW MATERIALS LLC

112 West 56<sup>th</sup> Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: [sales@irmwax.com](mailto:sales@irmwax.com) Website: [www.irmwax.com](http://www.irmwax.com)

### INDRAWAX 021-E

**Indrawax 021-E** is high molecular weight slack wax that has very low volatility characteristics. It is made to meet the volatility requirements of the board industry.

Indrawax 021-E can be used as sizing agent in the manufacture of composite wood panels where low smoke formation and good board surface quality are required.

### SPECIFICATIONS

Property	Method	Min	Max	Typical
Congealing point, °F (°C)	D-938	136.5 (58.0)	151.0 (66.1)	141.0 (60.5)
Oil content, wt%	D-721	-	25.0	13.2
Color, ASTM	D-1500	-	3.0	0.5
Viscosity @ 210°F, cSt	D-445	-	-	6.5
Flash point COC, °F (°C)	D-92	464 (240)	-	500 (260)

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.