



## INDUSTRIAL RAW MATERIALS LLC

112 West 56<sup>th</sup> Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: [sales@irmwax.com](mailto:sales@irmwax.com) Website: [www.irmwax.com](http://www.irmwax.com)

### INDRAWAX 097

**Indrawax 097** is a 100°F melt point slack wax.

Indrawax 097 can be used as sealing agent for wood products.

### SPECIFICATIONS

Property	Method	Min	Max	Typical
Solid point, °F (°C)	-	93 (34)	100 (38)	97 (36)
Gravity, °API	D-1298A	-	-	44.7
Oil content, wt%	D-721	-	10.0	6.0
Viscosity @ 100°C, cSt	D-445	2.0	2.5	2.3
Flash point COC, °F (°C)	D-92	350 (176.5)	400 (204.5)	365 (185)

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.