



## INDUSTRIAL RAW MATERIALS LLC

112 West 56<sup>th</sup> Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: [sales@irmwax.com](mailto:sales@irmwax.com) Website: [www.irmwax.com](http://www.irmwax.com)

### TYPICAL SPECIFICATIONS

#### INDRAWAX 5658-SC

TEST	METHOD	RESULTS
MELTING POINT	D-87	132 – 137°F (56 – 58°C)
OIL CONTENT wt%	D-721	1.5 Maximum
PENETRATION @ 77°F	D-1321	15 - 17
COLOR, SAYBOLT	D-156	+ 17 Minimum

### TECHNICAL DATA SHEET

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.