



INDUSTRIAL RAW MATERIALS LLC

112 West 56th Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: sales@irmwax.com Website: www.irmwax.com

INDRAWAX 8070

Indrawax 8070 is a C24-28 alpha olefin.

Indrawax 8070 can be used for applications such as candles, lube-oil additive, pour point depressant, polymers, PVC lubricants and others.

SPECIFICATIONS

Property	Method	Min	Max	Typical
Melting point, °F (°C)	D-127	-	-	151 (66)
Congearing point, °F (°C)	D-938	-	-	126 (52)
Color, Saybolt	D-156	+25	-	-
Appearance	D-4176	-	-	Clear and Bright
Penetration @ 77°F, dmm	D-1321	-	-	59
Penetration @ 110°F, dmm	D-1321	-	-	162
Viscosity @ 210°F, cSt	D-445	-	-	2.5
Flash point PMCC, °F (°C)	D-93	-	-	425 (218)
C ₂₂ content, wt. %	GLC	-	2.0	0.8
C ₂₂₋₂₈ content, wt. %	GLC	72.0	-	79.3
C ₃₀₊ content, wt. %	GLC	-	24.0	19.9

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.