



INDUSTRIAL RAW MATERIALS LLC

112 West 56th Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: sales@irmwax.com Website: www.irmwax.com

INDRAWAX 84-SLK

Indrawax 84-SLK is a slack wax with a melting point of 120°F.

Applications for Indrawax 84-SLK include : additives to sealers and emulsions, fire logs, and other applications needing high oil content.

SPECIFICATIONS

Property	Method	Min	Max	Typical
Melting point, °F (°C)	D-87	118 (47.8)	123 (50.5)	120 (49.0)
Gravity, °API	D-1298A	-	-	40.9
Oil content, wt%	D-721	3.0	9.0	6.0
Color, ASTM	D-1500	-	-	<1.0
Viscosity @ 100°C, cSt	D-445	3.2	4.0	3.7
Flash point COC, °F (°C)	D-92	410 (210)	440 (227)	430 (221)

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.