



INDUSTRIAL RAW MATERIALS LLC

112 West 56th Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: sales@irmwax.com Website: www.irmwax.com

INDRAWAX 850-BS

Indrawax 850-BS is a mid-range melting point petroleum slack wax.

SPECIFICATIONS

Property	Method	Min	Max	Typical
Melting point, °F (°C)	D-87	-	-	149 (65)
Congealing point, °F (°C)	D-938	-	-	142 (61)
Penetration @ 77°F, dmm	D-1321	-	-	61
Oil content, wt%	D-721	-	10.0	8.0
Color, Saybolt	D-156	-	-	-16
Color, ASTM	D-1500	-	-	1.0
Viscosity @ 210°F, cSt	D-445	-	-	7.61
Flash point COC, °F (°C)	D-92	-	-	525 (274)

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.



INDUSTRIAL RAW MATERIALS LLC

112 West 56th Street, New York, NY 10019 Telephone: (212) 688-8080

Fax: (212) 759-3696

Email: sales@irmwax.com Website: www.irmwax.com

Every care has been taken in the presentation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

Industrial Raw Materials LLC.