



## INDUSTRIAL RAW MATERIALS LLC

39 West Mall, Plainview, NY 11803  
T: (212) 688-8080 F: (212)-246-0158  
[irm@irmwax.com](mailto:irm@irmwax.com) [www.irmwax.com](http://www.irmwax.com)

# INDRAWAX 51-AS

Petroleum Slack Wax

Test Results (these are also typical)

| Property                  | Method ASTM | Test Result     |
|---------------------------|-------------|-----------------|
| Congealing point, °F (°C) | D-938       | 122 F° (50 C°)  |
| Oil content, wt.%         | D-721       | 13.2            |
| Viscosity @ 212°F, cSt    | D-445       | 3.6             |
| Color, ASTM               | D-1500      | 0.5             |
| Flash point, °F (°C)      | D-92        | 428 F° (220 C°) |

- Availability: Liquid Bulk, Tank Cars or Tank Wagon
- Steadiness of Supply: Assured
- Variability of quality: Consistent
- Price: Competitive
- Contact: Guy Morra or Eddie Wu or Edgar Torres
- Phone/ E-mail: 212-688-8080 / [irm@irmwax.com](mailto:irm@irmwax.com)

